

Pro Tour Plus

Data Sheet

Description

Composite acrylics tennis court surface, poured-in-place. A mixture of silicas, in-depth colouring pigments and resin binders, applied on a pre-fabricated roll-out shock-absorbing pad, in one black base layer, two base layers (the first black, the second coloured) and one layer of Finish coat. Textured white lines painted on Finish coat.

Use

Outdoor and Indoor Tennis Courts

Base support layer

Hot-rolled bituminous asphalt, aggregate size 0/4 to 0/6 mm. The evenness of the surface should be checked and variations in surface level should be no more than 4 mm over a 3 m length. Levelling and patching should be carried out using **FieldTurf Tarkett** Levelling Slurry only.

Characteristics of the court surface

| Description | kg/m ² * | Density |
|--------------------------|---------------------|---------|
| Primary Black Base layer | 1,00 | 1,65 |
| Shock absorption pad: | | |
| Black Base | 1,00 | 1,65 |
| Colour Base | 0,54 | 1,65 |
| Finish Coat | 0,48 | 1,50 |
| Total | 3,02 | |

* The above quantities should be read as an average rate of coverage for one court, prior to any dilution if applicable.

Binders

Composite Acrylics

Principal Charge

Silicas (Base and Finish coats)

Colouring

Fine rubber elements

Colours

In depth

Green, Dark Green (obtained by colouring additive)

Burgundy, Dark Burgundy (obtained by colouring additive)

Blue, Dark Blue (obtained by colouring additive)

Line Paint

Textured White Paint, supplied by **FieldTurf Tarkett** only.

Packaging

Base and Finish products: 25 kg metal drums

Primer: 25 kg metal drums

Line paint: 5 kg metal drums

Shelf life

12 months in original unopened drums, with batch codes. Drums should be protected from freezing, direct sunlight, excessively high temperatures and excessive humidity.

Speed of ball bounce

(Angular rebound as per ITF tests)

Medium

Guaranty

5 years, as set out in Tarkett Sport's general conditions of sale, available on request

Maintenance

According to maintenance instructions

Application

According to application instructions

Laying time

3 to 4 days for application, following a 2 week waiting period to allow for the curing of the asphalt, or for drying if a concrete base is used.

We reserve the right to modify these specifications.